

## 玻纤增强 PPS (RF-5031GF40)

PPS with glass fiber reinforced (RF-5031GF40)

### 一般信息

#### General Information

特征 Features	<ul style="list-style-type: none"> <li>● 优良的机械性能</li> <li>● 耐化学腐蚀性</li> <li>● 高耐热性</li> <li>● 尺寸稳定</li> </ul>	<ul style="list-style-type: none"> <li>Excellent mechanical property</li> <li>Excellent chemical resistance</li> <li>High heat resistance</li> <li>Good Dimensional Stability</li> </ul>
应用 Uses	<ul style="list-style-type: none"> <li>● 电子连接器/传感器</li> <li>● 仪表部件/外壳</li> <li>● 水泵叶轮/泵阀外壳</li> <li>● 家电/汽车部件</li> </ul>	<ul style="list-style-type: none"> <li>Electrical connector and sensor</li> <li>Assembly unit and shell</li> <li>Impeller and shell of pump valve</li> <li>Components for household appliances and automobiles</li> </ul>
形态 Forms	<ul style="list-style-type: none"> <li>● 粒子</li> <li>● Pellets</li> </ul>	
加工方法 Processing Method	<ul style="list-style-type: none"> <li>● 注塑</li> <li>● Injection Molding</li> </ul>	
RoHS	<ul style="list-style-type: none"> <li>● RoHS 合规</li> </ul>	Meet the RoHS specification

### 产品性能

#### Typical Properties

		测试标准 Test standard	测试条件 Test Condition	典型值 Typical Value
物理性能 Physical	熔融指数 Melt Flow Index	ASTM D1238	343°C/2.16kg	46g/10min
	密度 Specific Gravity	ASTM D792	23°C	1.68g/cm <sup>3</sup>
	成型收缩率 Mold Shrinkage	ASTM D955	23°C	0.2-0.5%
力学性能 Mechanical	拉伸强度 Tensile Strength	ASTM D638	50mm/min	192MPa
	断裂伸长率 Tensile Elongation	ASTM D638	50mm/min	1.7%
	弯曲强度 Flexural Strength	ASTM D790	2.0mm/min	290MPa
	弯曲模量 Flexural Modulus	ASTM D790	2.0mm/min	14850MPa
	悬臂梁缺口冲击强度 Izod Notched Impact Strength	ASTM D256	23°C	125J/m
	摩擦系数	ASTM D1894	VS. 钢	0.26
	磨耗量	ASTM D1044		49mg/1000 回
热性能 Thermal	热变形温度(未退火) Heat Deflection Temperature (Unannealed)	ASTM D648	1.80MPa	265°C

电气性能 Electrical	表面电阻率 Surface resistivity	ASTM D 257		1.5E+15 ohms.cm
	介电强度 Dielectric strength	ASTM D 149		20KV/mm
	介电常数 Dielectric constant	ASTM D 150	1MHz	4.1
燃烧性能 Burning	阻燃性能 Flame retardant	UL 94	0.4mm	V0
<b>加工信息 Processing Guidelines</b>				
	干燥条件 Drying	130-150°C, 3.0h		
	后段温度 Rear Temperature	290°C		
	中段温度 Middle Temperature	300°C-330°C		
	前段温度 Front Temperature	300°C-330°C		
	喷嘴温度 Nozzle Temperature	310°C-330°C		
	熔体温度 Melt Temperature	300°C-320°C		
	模温 Mold Temperature	140°C		

**备注:**

**Note:**

- 所有数据为实验室典型值，仅供参考，不作为产品标准。  
All data are typical values from laboratory. The data are used for reference only, not as production standard.
- 生产时避免材料和其他材料、灰尘及杂物接触。  
Avoid contact with other materials, dust and debris in the injection processing.
- 注塑时避免材料长时间停留在螺杆中。  
Avoid long time stay in the barrel in the injection processing.